

IRONASH

Light brownish straw coloured. Has a moderately course texture with straight grain with some gum veins. Quartersawn.

Applications: Cladding - Fins - Battens

Origin	Victoria
Botanical Name	Eucalyptus delegatensis & regnans
Density (Dry)	660kg/m ³
Above Ground Durability	Very High - Class 1 (H3 treated)
In Ground Durability	Low - Class 4
Hardness	Moderate - Janka 5.5
Sustainability	PEFC certification
Machining	Good
Gluing	Good
Unit Movement Tangential	0.23%
In Service Movement	Low
Termite Resistance	Resistant (H3 treated)
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available set lengths finger jointed
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

