

KARRI

Pale pink to redish brown. The timber has a course texture with interlocking and straight grain.

Applications: Structural

Origin	Western Australia
Botanical Name	Eucalyptus diversicolour
Density (Dry)	900kg/m ³
Above Ground Durability	High - Class 2
In Ground Durability	Moderate - Class 3
Hardness	Hard - Janka 9.0
Sustainability	No certification available
Machining	Good
Gluing	Good
Unit Movement Tangential	0.40%
In Service Movement	High
Termite Resistance	Not Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available set lengths
Fire Resistance	Group 3
Bushfire Attack Level	12.5 & 19. All AS3959 required applications

