

# MARRI

Yellow to pale brown. The timber course but even texture with interlocking grain. Distinctive vein structure.

## Applications: Furniture - Flooring

|                               |   |
|-------------------------------|---|
| Origin                        | Western Australia                           |
| Botanical Name                | Corymbia calophylla                         |
| Density (Dry)                 | 855kg/m <sup>3</sup>                        |
| Above Ground Durability       | Moderate - Class 3                          |
| In Ground Durability          | Moderate - Class 3                          |
| Hardness                      | Hard - Janka 7.1                            |
| Sustainability                | No certification available                  |
| Machining                     | Good  |
| Gluing                        | Good  |
| Unit Movement Tangential      | 0.34%                                       |
| In Service Movement           | Moderate                                    |
| Termite Resistance            | Not Resistant                               |
| Sapwood Lyctid Susceptibility | Susceptible                                 |
| Length Range                  | Usually random lengths                      |
| Fire Resistance               | Group 3                                     |
| Bushfire Attack Level         | 12.5 & 19. All AS3959 required applications |

