

OREGON

Yellow through to dark redish brown. Has a coarse uneven texture with moderately straight grain.

Applications:

Joinery - Cabinetry - Furniture - Structural

Origin	North America
Botanical Name	Pseudotsuga menziesi (Also known as Douglas Fir)
Density (Dry)	550kg/m ³
Above Ground Durability	Low - Class 4
In Ground Durability	Low - Class 4
Hardness	Soft - Janka 3.5
Sustainability	PEFC certification
Machining	Good
Gluing	Good
Unit Movement Tangential	0.26%
In Service Movement	Low
Termite Resistance	Not Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Usually available set lengths
Fire Resistance	Group 3
Bushfire Attack Level	Not tested

