

RECYCLED BLACKBUTT

Generally pale brown to golden yellow with an even texture, grain can be interlocking but generally straight. Gum veins and surface checking is to be expected.

Applications:

Joinery - Cladding - Linings - Structural

Origin	New South Wales & Queensland
Botanical Name	Eucalyptus Pilularis
Density (Semi Dry)	1000kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	High - Class 2
Hardness	Hard - Janka 9.1
Sustainability	Recycled
Machining	Good
Gluing	Good
Unit Movement Tangential	0.37%
In Service Movement	High
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Not Susceptible
Length Range	Random & set lengths available
Fire Resistance	Group 3
Bushfire Attack Level	12, 5 19 and 29. All AS3959 required applications.

