

RECYCLED IRONBARK BLEND

Light grey through to deep red brown. Moderately coarse and even, grain usually straight and occasionally interlocked

Applications:

Decking - Cladding - Joinery - Structural

Origin	New South Wales & QLD
Botanical Name	Eucalyptus paniculata & siderophloia
Density (Semi Dry)	1200kg/m ³
Above Ground Durability	Very High - Class 1
In Ground Durability	Very High - Class 1
Hardness	Very Hard - Janka 16.0
Sustainability	Recycled
Machining	Difficult
Gluing	Difficult
Unit Movement Tangential	0.39%
In Service Movement	High
Termite Resistance	Resistant
Sapwood Lyctid Susceptibility	Not susceptible
Length Range	Random & set lengths available
Fire Resistance	Group 3
Bushfire Attack Level	12.5 AND 19. All AS3959 required applications

